



Jmenovitý průměr d	Hmotnost [kg/m]	Průřez [mm²]	Minimální vztažná plocha fR
4,0	0,099	12,6	0,035 mm
5,0	0,154	19,6	0,035 mm
6,0	0,222	28,3	0,035 mm
8,0	0,395	50,3	0,040 mm
10	0,617	78,5	0,040 mm
12	0,888	113,0	0,040 mm
14	1,210	154,0	0,056 mm
16	1,580	201,0	0,056 mm
18	1,998	254,5	0,056 mm
20	2,466	314,2	0,056 mm
22	2,984	380,1	0,056 mm
25	3,853	490,9	0,056 mm
28	4,834	615,8	0,056 mm
32	6,310	804,3	0,056 mm
36	8,903	1015,0	0,056 mm
40	9,865	1194,6	0,056 mm
50	9,865	1693,5	0,056 mm